

5454 H34 Aluminum Sheet

Properties

General

Property	Temperature	Value	Comment
Density	23.0 °C	2.65 - 2.7 g/cm³	Typical for Wrought 5000 Series Aluminium

Mechanical

Property	Temperature	Value	Comment
Elastic modulus	23.0 °C	69 - 70 GPa	Typical for Wrought 5000 Series Aluminium
Elongation A100	23.0 °C	4 - 9 %	
Elongation A50	23.0 °C	4 - 10 %	
Hardness, Brinell	23.0 °C	81 [-]	
Plane-Strain Fracture Toughnes	23.0 °C	22 - 35 MPa·√m	Typical for Wrought 5000 Series Aluminium
Poisson's ratio	23.0 °C	0.33 [-]	Typical for Wrought 5000 Series Aluminium
Shear modulus	23.0 °C	26 - 26.5 GPa	Typical for Wrought 5000 Series Aluminium
Tensile strength	23.0 °C	270 - 325 MPa	

Yield strength
Rp0.2

23.0 °C

[200 - 240 MPa](#)

Thermal

Property	Temperature	Value	Comment
Coefficient of thermal expansion	23.0 °C	2.2E-5 - 2.5E-5 1/K	Typical for Wrought 5000 Series Aluminium
Max service temperature		150 °C	Typical for Wrought 5000 Series Aluminium
Melting point		560 - 655 °C	Typical for Wrought 5000 Series Aluminium
Specific heat capacity	23.0 °C	879 - 963 J/(kg·K)	Typical for Wrought 5000 Series Aluminium
Thermal conductivity	23.0 °C	112 - 205 W/(m·K)	Typical for Wrought 5000 Series Aluminium

Electrical

Property	Temperature	Value	Comment
Electrical conductivity	23.0 °C	1.80E+7 - 3.10E+7 S/m	Typical for Wrought 5000 Series Aluminium
Electrical resistivity	23.0 °C	3.3E-8 - 5E-8 Ω·m	Typical for Wrought 5000 Series Aluminium

Chemical properties

Property	Value
Chromium	0.05 - 0.2 %
Copper	0.1 %
Iron	0.4 %

Magnesium	2.4 - 3 %
Manganese	0.5 - 1 %
Other	each 0.05, total 0.15, Rest Al
Silicon	0.25 %
Titanium	0.2 %
Zinc	0.25 %

Technological properties

Property	
Brazing	general: no brazing is known or developed
Corrosion properties	Stress corrosion cracking: no damage during operation and laboratory tests, general: very good, without protection in industrial or seawater atmosphere
General machinability	General: poor (O, H32, H111), sufficient (H34)
Workability	general (condition): good (O), acceptable (H32, H34, H111)